



Škoda Rapid Sedan 2013 → PU Side Mouldings F-46



nad przetłoczeniem
over the line
über dem Strich

RH FRONT RH REAR



← FRONT



LH FRONT LH REAR

Degrease/entletten/degraisser/ontvetten
Alcohol/Alkohol/Alcool/Alcohol

1



20-40 °C

2




48h



5



3




4



ledere cm goed aandrukken !!
Press very carefully every cm !!
Sehr fest andrücken jeden cm !!

0-1 mm.

A



4-5 mm.